

COBBLESTONE COLLECTION

Color shading
V2 Slight



Formati
Sizes

± 9 mm

60×60/24"×24" R

Caratteristiche/Features/Caracteristiques/Eigenschaften/Eigenschappen/Características
Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

	Regulation	Required standards	Value
 Dimensioni/Sizes/Dimensions/ Abmessungen/Afmetingen/ Dimensiones	UNI EN ISO 10545/2	Non rettificato Not rectified ± 0.5 % max 2mm ± 0.3 % max 1mm Spessore/Thickness/Epaisseur/ Stärke/Dikte/Crosor ± 5 % max 0.5mm ± 5 % max 0.5mm Rettilineità spigoli/Linearity/Rectitude des arêtes/ Kantengeradheit/Rechtheid kanten/Rectitud de los lados ± 0.5 % max 1.5mm ± 0.3 % max 0.8mm ** Ortogonalità/Wedging/Orthogonality/ Rechtwinkligheid/hoekshoed hoeken/Ortogonalidad ± 0.5 % max 2mm ± 0.3 % max 1.5mm Planarità/Warpage/Planité/Ebenfächigkeit/ Vlakheid/Plantud ± 0.5 % max 2mm ± 0.4 % max 1.8mm	Rettificato * Rectified * Conforme Compliant
 Assorbimento acqua/Water absorption/Absorption d'eau/ Wasseraufnahme/Waterabsorptie/ Absorción de agua	UNI EN ISO 10545/3	≤ 0.5 %	0.2%
 Resistenza alla flessione/Flexual Strenght/Résistance à la flexion/ Biegefestigkeit/Buigvastheid/ Resistencia a la flexión	UNI EN ISO 10545/4	≥ 35 N/mm² S ≥ 1300 N (thickness ≥ 7.5 mm)	Conforme Compliant Conforme Compliant
 Coefficiente di restituzione (COR)/ Coefficient of restitution (COR)/ Coefficient de restitution (COR)/ Schlagfestigkeit (COR)/ Restitutiecoëfficiënt (COR)/ Coeficiente de restitución (COR)	UNI EN ISO 10545/5	Valore consigliato ≥ 0.55/ Recommended value ≥ 0.55/ Valeur recommandée ≥ 0.55/ Empfohlener Wert ≥ 0.55/ Aanbevolen waarde ≥ 0.55/ Rvalor recomendado ≥ 0.55	Conforme Compliant
 Resistenza all'abrasione profonda/ Deep abrasion resistance/Resistance à l'abrasion/ Widerstand gegen Tiefenverschleiß/ Weerstand tegen afschuren/ Resistencia a la abrasión profunda	UNI EN ISO 10545/6	≤ 175 mm ³	Conforme Compliant
 Resistenza all'abrasione/ Abrasion resistance/ Résistance à l'abrasion/ Abriebbeständigkeit/ Weerstand tegen afschuring/ Resistencia a la abrasión	UNI EN ISO 10545/7	PEI Solo per piastrelle smaltate / Only for glazed tiles	
 Coefficiente di dilatazione termica lineare/Coefficient of thermal linear expansion/Coefficient de dilatation thermique linear/Lineare Wärmeausdehnungskoeffizient/ Lineaire thermische uitzetting/ Coeficiente de dilatación termica linear	UNI EN ISO 10545/8	Metodo di prova disponibile/Tests method available/ Methode d'essai disponible/Verfügbares/Prüfverfahren/ Testmethode beschikbaar/Método de prueba disponible	≤ 7 · 10 ⁻⁴ °C ⁻¹
 Resistenza agli sbalzi termici/ Thermal shock resistance/Resistance aux écarts de temperature/ Temperatuurschokbeständigkeit/ Temperatuurswisselingen/Resistencia al choque térmico	UNI EN ISO 10545/9	Nessun campione deve presentare difetti visibili/ No sample must show visible defects/ Aucun échantillon ne doit présenter des défauts visibles/ Kein Exemplar darf sichtbare Schäden aufweisen/ Geen enkel monster mag zichtbare gebreken vertonen/ Ninguna muestra debe presentar defectos visibles	Conforme Compliant
 Dilatazione all'umidità/Moisture expansion/Dilatation à l'humidité/ Feuchtigkeitsausdehnung/Uitzetting door vocht/Dilatación por la humedad	UNI EN ISO 10545/10	Metodo di prova disponibile/Tests method available/ Methode d'essai disponible/Verfügbares/Prüfverfahren/ Testmethode beschikbaar/Método de prueba disponible	≤ 0.01 % (0.1 mm/m)
 Resistenza al fuoco/ Fire resistance/ Résistance au feu/ Brandverhalten/ Brand weerstand/ Resistencia al fuego	UNI EN ISO 13501-1	Dichiarare un valore / Declare a value Classe A1 oppure A_{1,s} / Class A1 or A_{1,s}	A _{1,s}
 Resistenza al gelo/Frost resistance/ Résistance au gel/Frostbeständigkeit/ Vorstbeständigkeit/ Resistencia a la helada	UNI EN ISO 10545/12	Resistenti/Resistant/Resistants/ Widerstandsfähig/ Weerbaarstig/Resistentes	Conforme Compliant

TORONTO
115 Carnarvon Street
Toronto, ON M6M 3C9
T 416 413 9008
F 416 413 9652

TROY
1700 Stutz Drive, Ste 92 & 94
Troy, MI 48084
T 248 643 6520
F 248 643 6523

Please note, all specifications have been supplied
by the manufacturer and are subject to change.

Email: mail@cercantile.com
Website: www.cercantile.com

COBBLESTONE COLLECTION

Caratteristiche/Features/Caracteristiques/Eigenschaften/Eigenschappen/Características Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

	Regulation	Required standards	Value
 Resistenza all'attacco chimico/ Chemical resistance/Resistance à l'attaque chimique/Beständigkeit gegen Chemikalien/Chemische bestandheid/Resistencia al ataque químico	UNI EN ISO 10545/13		
	Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina / Resistance to household chemicals and swimming pool salts	Classe minima B (GB per piastrelle smaltate) / Minimum class B (GB for glazed tiles) Classe minima B (UB per piastrelle non smaltate) / Minimum class B (UB for unglazed tiles)	A
	Resistenza a basse concentrazioni di acidi e alcali / Resistance to low concentrations of acids and alkalis	Dichiarare una classe / Declare a class Metodo di prova disponibile / Tests method available	LA
	Resistenza ad alte concentrazioni di acidi e alcali / Resistance to high concentrations of acids and alkalis	Dichiarare una classe / Declare a class Metodo di prova disponibile / Tests method available	HA
 Resistenza alle macchie/Stain resistance/Insensibilité aux taches/ Beständigkeit gegen Fleckenbildner/ Substanzen/Weerstand tegen vlekken/ Resistencia a las manchas	UNI EN ISO 10545/14	UGL Dichiarare un valore / UGL Declare a value	Classe 5 Class 5
		GL ≥ 3	
 Pb Cd Cessione di piombo e cadmio/ Lead and cadmium discharge/ Perte de plomb et cadmium/ Abgabe von Blei und Cadmium/ Ontdaan van lood en cadmium/ Cesión de plomo y cadmio	UNI EN ISO 10545/15	Valore dichiarato per piastrelle GL / Declared value for GL tiles	
 Indicazione di resistenza allo scivolamento/Assessment of slip resistance/Indication de la résistance au glissement/ Bestimmung der Trittsicherheit/ Indicatie voor de slipvastheid/ Indicación de resistencia al deslizamiento	DIN 51130	Dichiarare un valore (R) / Declare a value (R)	R10 R11 OUT20
	DIN 51097	Dichiarare un valore (A+B+C) / Declare a value (A+B+C)	
	BS 7976-2:2002 (CEN/TS 16165, Annex C) Pendulum Friction Test	Dichiarare un valore / Declare a value	
 Coefficiente di attrito dinamico/ Measurement of dynamic coefficient of friction/Mesure du coefficient de frottement dynamique/Messung des dynamischen Reibungskoeffizienten/ Meting van de dynamische wrijvingscoefficient/Coefficiente de rozamiento dinámico	BCRA Rep CEC/81	Asciutto > 0,40 / Bagnato > 0,40	Asciutto > 0,40 / Bagnato > 0,40
	ANSI A137.1-2012 (BOT3000)	> 0,42 Wet	> 0,42 Wet

TORONTO
115 Carnarvon Street
Toronto, ON M6M 3C9
T 416 413 9008
F 416 413 9652

TROY
1700 Stutz Drive, Ste 92 & 94
Troy, MI 48084
T 248 643 6520
F 248 643 6523

Please note, all specifications have been supplied by the manufacturer and are subject to change.

Email: mail@cercantile.com
Website: www.cercantile.com